



#1380
GLAZE-N-SEAL

PRODUCT DESCRIPTION

Glaze-N-Seal was designed to seal and protect Epoxy bonded natural stone surfaces such as Chattahoochee Stone, River Rock, and their supporting members such as retainers and expansion joints. It seals surfaces and helps protect them from moisture and standing water.

PRODUCT ADVANTAGES

! Ease of application ! excellent sealing qualities ! Mildew resistant

LIMITATIONS

CONTAINS PETROLEUM DISTILLATE. Keep away from heat, sparks, and flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, wear respiratory protection (NIOSH/MSHA TC 23 C or equivalent), or leave the area. Close container after each use. Avoid contact with skin. FIRST AID: If swallowed, do not induce vomiting. Call physician immediately. USE WITH ADEQUATE VENTILATION.

MATERIAL PREPARATION

Glaze-N-Seal does not need stirring. Apply as it comes in the container. Do not add oil or other paints.

SURFACE PREPARATION

It is essential that surfaces be clean. Normally scrubbing with detergent and a stiff bristle brush followed by through rinsing with clean water will prepare surfaces. If surfaces are very dirty and oily and will not clean as above, use a stronger detergent (TSP type) and a pressure washer. If mildew is present treat with a mildew remover, rinse thoroughly, let dry before sealing. Surfaces should dry 1-2 days before application. Do not apply to damp or dewy surfaces or when surface temperatures are below 50°.

APPLICATION

Apply by solvent resistant roller or bristle brush of good quality. Apply evenly; two coats are recommended for best results. This product is intended to glaze the top surface of the stones. DO NOT saturate the surface with too much material. When applying by roller, apply Glaze-N-Seal with overlapping strokes in the same direction, eliminating missed surfaces. DO NOT run roller dry. Apply second coat of Glaze-N-Seal at right angle when the first coat is completely dry.

LIMITATION OF LIABILITY

Technical data is true and accurate at date of issuance, but subject to change without notice. Our products conform to **DYCO** quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor or other consequential damages is hereby excluded.

TECHNICAL DATA

Product Number - #1380

Generic Type - Oil Modified Urethane

Color - Clear

Sheen - Gloss

% Solids by Weight - 36.81%

% Solids by Volume 28.93%

Recommended Coverage:

4.0 mils wet

2.0 mils dry (calculated)

Avg 150-200 sq ft per gallon

% Vehicle Solids by Weight - 36.81%

% Pigment by Weight - 0.0%

% Solvent by Weight - 63.19%

Viscosity (Zahn Cup) - 18.23 Seconds

Weight/Gallon -7.12 lbs.

VOC - 539 grams/liter

Flash Point - 52 Deg. F.

Dry Time - 70 F., 50% R .H.

Touch - 30-60 minutes

Recoat - 2 to 2 2 hours

Reduction Solvent -

Not Recommended

Clean Up Solvent- Mineral Spirits
or VM&P NAPTHA

