



#1870
 ULTRA SPREAD
 MODIFIED ACRYLIC INTERIOR
 SATIN WALL & TRIM
 EGGSHELL

PRODUCT DESCRIPTION

Interior Eggshell Modified Acrylic enamel that is easy to apply, has excellent touch up qualities.

RECOMMENDED USES

Properly primed wood, drywall, plaster, stucco, cement, concrete, brick, and masonry surfaces.

PRODUCT ADVANTAGES

- ! Ease of application ! Fast drying ! Water clean up
- ! Non-yellowing ! Washable ! Low Odor

MATERIAL PREPARATION

Stir from bottom with vigorous strokes. Do not add oil or other paints.

LIMITATIONS

If two coats are needed, allow first coat to dry 1 hour before applying finish coat. Do not apply when temperature is below 45E F. Protect from freezing.

SURFACE PREPARATION - SURFACE PROBLEMS

Mildew - Treat with a mildew remover, rinse thoroughly, let dry before painting. **Efflorescence** - (whitish deposit on masonry surfaces) treat with solution of 3 parts water to 1 part muriatic acid. Let sit 15 minutes then rinse before painting. **Chalk** - Remove by hand scrubbing or pressure cleaning. Apply a chalk bonding primer, allow to dry thoroughly then apply paint.

SURFACE PREPARATION - SURFACE TO BE REPAINTED

The surface to be repainted must be free of any loose paint, grease, dirt, rust, or other adherent surface contaminants. Cleaning may be accomplished by using a detergent solution, scraping, or wire brushing. The method of cleaning is based on the surface and substance being removed. Any glossy surface must be dulled by lightly sanding or use of a solvent etch.

APPLICATION

Brush, roller, or spray.

PRIMERS

Chalky Surfaces - Use DYCO #1315 Sure Prep. **Masonry** (porous unpainted) Use DYCO # 990 Block filler. **Wood** (unpainted - interior) - Use DYCO #1445 Enamel undercoater.

Product Number - #1870

Generic Type - Vinyl Acrylic

Color - White

Sheen - Eggshell

% Solids by Weight - 52.09%

% Solids by Volume - 37.11%

Recommended Coverage:

4.0 mils wet

1.3 mils dry

Avg 200-350 sq ft per gallon

% Vehicle Solids by Weight - 20.75%

% Pigment by Weight - 31.34%

% Solvent by Weight - 47.91%

Viscosity (Stormer) - 95-97 KU

Weight/Gallon - 10.95 lbs

Flash Point - None

Dry Time - 70E F., 50% R .H .

Touch - 30 minutes

Recoat - 45-60 minutes

Reduction Solvent - Water

Clean Up Solvent- Water

Tinting - Colortrend Que System

1870 White/Pastel

1871 Tint Base

1872 Deep Base

1873 Ultra Deep

LIMITATION OF LIABILITY

Technical data is true and accurate at date of issuance, but subject to change without notice. Our products conform to **DYCO** quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor, or other consequential damages is hereby excluded.

