



#2202
SILICONE ALKYD
INDUSTRIAL S/G ENAMEL

PRODUCT DESCRIPTION

Industrial Semi-Gloss Enamel is a Silicone Alkyd product with superior gloss and color retention. The product is formulated with superior film properties to provide a smooth semi-gloss finish that will withstand severe weathering.

RECOMMENDED USES

Properly primed metal, masonry, brick, plaster, and wood.

PRODUCT ADVANTAGES

*Superior Gloss Retention *Superior Color Retention
*Ease of Application *Excellent Protection to All Surfaces

MATERIAL PREPARATION

Stir from bottom with vigorous strokes to mix. Do not add oil or other paints.

LIMITATIONS

CAUTION: Combustible. Contains petroleum distillates. Avoid contact with eyes and prolonged contact with skin. Use only in a well ventilated area. Do not use near heat, sparks, or flame.

SURFACE PREPARATION - SURFACE PROBLEMS

Surface preparation is simple, consisting of providing a clean surface to ensure maximum results. Rust and grease should be removed from metal surfaces by use of sand blasting, but if this is not feasible use wire brush, steel wool or industrial abrasive paper. On old paint, surfaces remove loose paint and chalking by sanding or wire brushing. Prime all unpainted metal surfaces with **DYCO 1972 Red or DYCO MP50 White** Rust Inhibitor Primer (or equivalent), to ensure maximum adhesion and protection.

APPLICATION

2201 Enamel may be applied by brushing, rolling, or spraying. For spraying, reduce with mineral spirits if needed. Use also for cleaning brushes, rollers and spray equipment.

LIMITATION OF LIABILITY

Technical data is true and accurate at date of issuance, but subject to change without notice. Our products conform to DYCO quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor or other consequential damages is hereby excluded.

TECHNICAL DATA

Product Number - #2202

Generic Type-Modified Silicone Alkyd

Color - White
Sheen - Semi Gloss

% Solids by Weight - 67.77%
% Solids by Volume - 49.22%

Recommended Coverage:
3.0 mils wet 1.5 mils dry
Avg. 200-400 sq.ft. per gallon

Practical Coverage
Avg. 300 sq.ft. per gallon

Vehicle Solids by Weight -
30.68%

Pigment by Weight - 37.08%
Solvent by Weight - 32.23%
Viscosity (Stormer) - 86-89 KU

Weight/Gallon - 10.68
Flash Point - 105° F.

Dry Time - 70° F., 50% R. H.
Touch - 2 hours
Recoat - 24 hours

Reduction Solvent - Mineral
Spirits

Clean Up Solvent - Mineral Spirits

2202- Tint Base
2204- Clear Base

