



**DYCO VERDE**  
40 WHITE TINT BASE  
INTERIOR FLAT  
ACRYLIC

**PRODUCT DESCRIPTION**

Dyco Verde is an environmentally inspired wall and trim paint that is solvent free, non-toxic and ultra low odor. Scrubbable, durable and soil resistant, Verde is an ideal finish for interior walls, ceilings and trim in any room. Recommended for plaster, drywall, masonry, non-stained, and painted or primed metal surfaces.

**SURFACE PREPARATION**

**Clean Surfaces**-Cleaning may be accomplished by using a detergent solution, scraping, or wire brushing.

**Repair Cracks**-Fill and patch cracks and surface imperfections with appropriate patching and caulking compounds.

**Water Clean up**-Clean tools in warm, soapy water immediately after use.

**SURFACE PROBLEMS**

**Mildew**- Treat with a mildew remover, rinse thoroughly, let dry before painting.

**Chalk**- Remove by hand scrubbing. Apply a chalk bonding primer, allow to dry thoroughly then apply paint.

**SURFACES TO BE REPAINTED**

The surface to be repainted must be free of any loose paint, grease, dirt, rust, or other adherent surface contaminants. The method of cleaning is based on the surface being removed. Any glossy surface must be dulled by lightly sanding and/or use of a deglosser.

**MIXING**

Stir thoroughly. Apply at 50° or above. **Application** – brush, roller, or spray.

**TECHNICAL DATA**

**Dry Time** - 70° F at 50% relative humidity Touch: 30 min; Complete Dry; 1hour.

**Coverage** - 200-400 sq. ft./gal. depending on surface texture.

**For Premium Performance – Apply Two Coats**

**Thinning**- Generally none required for brush or roller application.

For spray, add up to 1 pint of water per gallon.

**PRIMERS**

**Drywall** – DYCO 1055 Drywall Primer should be used to seal un-primed drywall or patching.

**Plaster** – Allow new stucco, plaster and masonry to cure 30 days before priming Use DYCO 1055 Primer to seal surface before painting.

**Stained Surfaces**- Use DYCO 6005 Stain Blocker.

**Wood**- On unpainted interior wall and trim, use DYCO 6005 Undercoater.

**Metal**- Prime with an appropriate primer before applying this product.

**LIMITATION OF LIABILITY**

Technical data is true and accurate at date of issuance, but subject to change without notice. Our products conform to **DYCO** quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor or other consequential damages is hereby excluded.

**TECHNICAL DATA**

Product Number - **#40**

Generic Type – 100% Acrylic Latex

Color - White

Sheen - Flat

% Solids by Weight – 59.88%

% Solids by Volume – 40.48%

Recommended Coverage:

4.0 mils wet

1.6 mils dry

Avg 200-400 sq ft per gallon

% Vehicle Solids by Weight – 13.60%

% Pigment by Weight – 46.28%

% Volatile by Weight – 40.12%

PVC – 55.82%

Viscosity (Stormer) -101-102 KU

Weight/Gallon – 12.41

Flash Point - None

Dry Time - 70E F., 50% R. H.

Touch - 45 minutes

Recoat - 1 hour

Reduction Solvent - Water

Clean Up Solvent - Water

Dyco VOC Free Tint

Tinting -

#40 – White Tint Base

#41 – Medium Base

#42 - Deep Tint Base

#43 – Neutral Base

