



**C22**

Clear Top Glaze

**PRODUCT DESCRIPTION**

C-22 Clear Top Glaze was designed to over coat Dyco's Tuff Coat Floor Coating.

**RECOMMENDED USES**

For previously coated Tuff Coat surfaces such as: patios, walkways, pool decks, garage floors & concrete. Ideal for protecting designs on driveways, etc. Not recommended for wood.

**PRODUCT ADVANTAGES**

\* Resists fading \* Resists cracking & peeling \* Resists mildew \* Easy to apply

**MATERIAL PREPARATION**

Stir from the bottom with vigorous strokes. Do not add oil or other paints. Do not use bristle brushes.

**LIMITATIONS**

Keep out of the reach of children. Do not take internally. If swallowed, contact physician immediately. Keep away from direct heat & open flame. DO NOT add non-skid additive to this clear product. Do not apply below 50°F or to a damp surface. Keep from freezing.

**SURFACE PREPARATION**

Top Coat Clear must be applied over a newly applied clean and dry surface, within 72 hours. Surface will be tack free in one hour, ready for foot traffic in 2 hours and vehicle traffic in 72 hours.

**APPLICATION**

Brush, Roll or Spray. When applying with a short nap roller (3/8" Nap) DO NOT APPLY excessive pressure on the roller, roll with light to medium pressure. Apply Top Coat Glaze evenly and do not leave puddles or roller marks. Only one coat is required. Do Not Apply to areas where standing water is evident. Where there is a possibility of slipperiness - DO NOT APPLY THIS PRODUCT. If there has been a skid, texture added to the base coat this product may perform properly but all precautions must be taken.

**LIMITATION OF LIABILITY**

Technical data is true & accurate at date of issuance, but subject to change without notice. Our products conform to DYCO quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor or other consequential damages is hereby excluded.

**TECHNICAL DATA**

Product Number - C22

Generic Type - Waterborne Acrylic

Color - Clear

Sheen - Gloss

% Solids by Weight - 27.67%

% Solids by Volume - 25.50%

Recommended Coverage:

Avg 300-500 sq. ft per gal on porous surfaces

% Vehicle Solids by Wt. - 27.67%

% Volatile by Weight - 72.33%

Viscosity #2 Zahn - 16-17 Sec.

VOC - 188 grams/liter  
1.57 lbs/gallon

Weight/Gallon - 8.54 lbs

Flash Point - N/A

Dry Time - 70° F, 50% RH

Touch - 1 hour

(Depending on weather)

Recoat - 2 hours

(High humidity and/or low temperatures will effect dry time).

Apply Above 50°F

Reduction Solvent - Water

Clean Up Solvent - Warm soapy water

KEEP FROM FREEZING

