



#MP-90
ACRYLIC MODIFIED ALKYD
PRIMER, QUICK DRY

PRODUCT DESCRIPTION

A quick dry non-lifting primer.

RECOMMENDED USES

For Steel or Galvanized surfaces where maximum corrosion resistance is needed. Can be top coated with Acrylic, Alkyd or Epoxy Ester type coatings. **MP-90** is ideal for new or repaint metal surfaces, whose rusted surface is properly prepared prior to application of primer. Recommended primer for **DYCO M3605 Series MetalMax Finish Coat.**

PRODUCT ADVANTAGES

! EASE OF APPLICATION ! EXCELLENT RUST INHIBITIVE QUALITIES
! FAST DRY

SURFACE PREPARATION

Remove all rust and mill scale by sandblasting, pickling or other acceptable means. Surfaces must be free of grease, oil and foreign matter.

APPLICATION

Brush, roller, conventional or airless spray. Do not apply if rain threatens. **PRECAUTIONS** - Take these precautions before the coating dries and during application: **CAUTION: CONTAINS XYLENE.** May be harmful or fatal if swallowed. **FLAMMABLE:** Keep away from heat, sparks and flame. To avoid breathing vapors or spray mist, open windows and doors or use forced ventilation to ensure entry of fresh air during application and drying. If you experienced eye watering, headaches or dizziness, leave the area or wear respiratory protection (NIOSH/MSHA TC 23C or equivalent). Avoid contact with skin. Close container after each use. **FIRST AID:** If swallowed, do not induce vomiting. Call physician immediately. **ANTIDOTES: EXTERNAL** - Flush eyes with water and get medical attention. Wash skin immediately with soap and water. **USE WITH ADEQUATE VENTILATION: NOTICE:** Reports have associated repeated and prolonged occupational overexposure to solvent with permanent brain damage and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. **KEEP OUT OF THE REACH OF CHILDREN**

LIMITATION OF LIABILITY

Technical data is true and accurate at date of issuance, but subject to change without notice. Our products conform to **DYCO** quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor, or other consequential damages is hereby excluded.

TECHNICAL DATA

Product Number - #MP-90
Generic Type – Acrylic Modified Alkyd
Color - Grey
Sheen - Satin
% Solids by Weight -71.25%
% Solids by Volume – 55.24%
Recommended Coverage:
4.4 mils wet
2 mils dry
Avg 250-350 sq ft per gallon
% Vehicle Solids by Weight - 29.45%
% Pigment by Weight -41.81%
% Solvent by Weight -28.75%
Viscosity (Stormer) – 76-77 KU
Weight/Gallon – 11.40 lbs
Flash Point - 81° F
Dry Time - 70° F - 50%RH
Touch - 45 minutes
Dry - 2 hours
Recoat – 4 hours
Maximum VOC - 450 - grams/liter
Reduction Solvent - DYCO ES110
Clean Up Solvent - Xylene

