



#TC-40
FLEXIBLE TEXTURE
BRUSH ON
CAULK/SEALANT

PRODUCT DESCRIPTION

#TC-40 is a texture multi-polymer sealant and caulk with superior film properties. Formulated to provide excellent adhesion, flexibility and durability.

RECOMMENDED USES

TC-40 can be applied to asbestos, wood, concrete, stucco, asphaltic surfaces, flexible foams and metals including aluminum, and galvanized. Caulking hairline cracks on exterior masonry.

PRODUCT ADVANTAGES

TC-40 can be used for vent pipe flashing, air conditioning installation, siding, cracks in wall, roof flashing and many more. TC-40 is a texture finish blend with stucco surfaces so that patches and filled cracks or joints will not be apparent after painting.

MATERIAL PREPARATION

Stir from bottom with vigorous strokes. Do not add oil or other paints.

LIMITATIONS

Do not apply when temperature is below 50° F. Protect from freezing.

SURFACE PREPARATION

Surface preparation is simple, consisting of providing a clean surface to ensure maximum results. Rust and grease should be removed with a wire brush, steel wool or industrial abrasive paper. On old paint surfaces remove loose paint and chalking by scraping, wire brushing or industrial cleaner. If surface is chalky use a chalk sealer prior to patching. On cracks over 2 inch it is advisable to use fiberglass tape. Apply to clean dry surfaces only.

APPLICATION

TC-40 may be applied by brush, towel or knife. Apply one inch on either side of crack one eighth of an inch thick. Clean tools with water.

LIMITATIONS OF LIABILITY

Technical data is true and accurate at date of issuance, but subject to change without notice. Our products conform to DYCO quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to re-placement of product or purchase price. Labor, cost of labor, or other consequential damages is hereby excluded.

TECHNICAL DATA

Product Number - #TC-40

Generic Type-Acrylic/Vinyl
Acrylic Blend

Color - White

Sheen - Flat

% Solids by Weight - 65.50%

% Solids by Volume - 54.36%

% Vehicle Solids by Weight-
28.33%

% Pigment by Weight - 37.17%

% Volatile by Weight - 34.50%

Viscosity- Thick

Weight/Gallon - 11.24 lbs.

Flash Point - None

Dry Time - 70° F., 50% R. H.
1-2 hours

Reduction Solvent -
Not recommended

Clean Up Solvent - Water

Brush Grade and
Trowel Grade

